



TECHNICAL DATA

PPL-06

SKID TEX ST30 NON-SKID ADDITIVE

DESCRIPTION AND USES

Skid Tex is an extremely fine mineral compound that when added to paint will provide a durable, non-skid finish in all types of floor paints. Skid Tex can be used in interior and exterior paints to help prevent slips and falls. Skid Tex will not change color or the performance properties of the paint.

PERFORMANCE CHARACTERISTICS

- Easy to use non-skid additive for paint
- Prevents slips and falls
- Can be used in interior and exterior floor paints

PRODUCTS

SKU	Description
76084	1-Quart

PRODUCT APPLICATION

SURFACE PREPARATION

Follow paint manufacturer's directions for surface preparation.

PRODUCT APPLICATION (cont.)

INSTRUCTIONS FOR USE

Apply only when air, material, and surface temperatures are between 50-90°F (10-32°C) and the relative humidity is below 85%. In a clean, separate container, add Skid Tex to the paint, in a proportion of one pound to one gallon of paint. Add ½ cup of Skid Tex for one quart of paint. Mix thoroughly using a slotted paint paddle or mechanical agitator to ensure the additive is incorporated. Let the mixture sit for at least 30 minutes before applying. Stir occasionally to ensure good distribution of the mixture. Use a ¾" to ¾" nap roller and follow the manufacturer's directions for paint application. If two coats of paint are used, Skid Tex may be used in both coats. For high gloss finishes, use Skid Tex in the first coat only then apply a high gloss topcoat.

CLEAN-UP

Follow paint manufacturer's directions for clean up and disposal.



TECHNICAL DATA

SKID TEX ST30 NON-SKID ADDITIVE

PHYSICAL PROPERTIES

Physical Properties		SKID TEX ST30 NON-SKID ADDITIVE
Composition		Pumice, Crystalline Silica
Weight	Per Gallon	20.3 lbs.
	Per Liter	2.43 kg
Solids	By Weight	100.0%
	By Volume	100.0%
Volatile Organic Compounds		0 g/l
Shelf Life		5 years
Practical Coverage		Will depend on the method of application and surface type
Flash Point		>200°F (93°C)
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.